

Preliminary Technical Sheet

HI-AIR® Brand Hook 066 Fastener

Material Description

Name: Hook 66-0399
Material: Nylon [Nomex® FR yarns]

Performance Characteristics

Testing	Typical Values
Closure Peel Strength after Laundering	0.78 PIW
Closure Shear Strength after Laundering	31.1 LBS.
Flammability Testing per FAR 25.853, 12 second	1.2 Burn Length Avg. 9.1 Flame Time Avg. 0.0 Drip Time Avg.

Tested with: Loop 003

Velcro® brand Hook 66-0399; meets the requirements of Mil-Spec A-A-55126 rev. B, Type 1, Class 2

The preparation, testing and conditioning follow the Velcro USA Inc. Quality Control Laboratory Standard Procedures.

Note: The following information should be considered representative and is intended to be used as a reference only. This information should not be used for specification purposes.

Rev. Date: 7/09/13