

A stiff, carbon thickened, light viscosity, polyolester grease intended for wide temperature applications where a degree of electrical conductivity in the grease is required.

Lubricant Properties		Typical value	Test Method
Recommended Service Range (°C)		-40 to 150	
Thickener		Carbon	
Base oil	Type	Ester	
	Kinematic viscosity	40°C 100°C	57 cSt 9 cSt
	Viscosity Index	142	ASTM D-2270
	Flash point	°C	285 ASTM D-92
	Pouring point	°C	-56 ASTM D-97
Typical Properties of the Grease		Typical value	Test Method
Color, Appearance		Black, Smooth	
Penetration (1/10 mm)	NLGI Grade	3	ASTM D-217
	Unworked	226	ASTM D-217
	Worked	60X 230	ASTM D-217
Density	25°C	1.06 g/cm ³	ASTM D-70
Oil Separation	24 hour(s)	100°C	0.2 ASTM D-6184
Evaporation	24 hour(s)	100°C	0.1

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1409)

Distributed by Newgate Simms Limited

Broughton Mills Road, Bretton, Chester, CH4 0BY, United Kingdom
+44(0)1244 660771 www.newgatesimms.com info@newgatesimms.com