

A PTFE thickened, medium viscosity, completely fluorinated grease for use in high temperature applications exposed to fuels or aggressive chemicals. It possesses excellent thermo-oxidative stability and low vapor pressure characteristics.

Ford: WSB-M1C242-A, GM: 9986173

Lubricant Properties		Typical value	Test Method
Recommended Service Range (°C)		-50 to 225	
Thickener		PTFE	
Base oil	Type	Perfluoropolyether	
(Uniflor 8510)	Kinematic viscosity	100°C	15.8 cSt
		40°C	65 cSt
	Viscosity Index		258
	Pouring point	°C	-54
		ASTM D-445	ASTM D-97
Typical Properties of the Grease		Typical value	Test Method
Color, Appearance		White, Smooth	
Penetration (1/10mm)	Worked	60X	281
			ASTM D-217
Density		25°C	1.95 g/cm ³
			NYE CTM
Oil Separation	24 hour(s)	150°C	6.8
			ASTM D-6184
Evaporation	24 hour(s)	150°C	1 %
			NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)

Distributed by Newgate Simms Limited

Broughton Mills Road, Bretton, Chester, CH4 0BY, United Kingdom
+44(0)1244 660771 www.newgatesimms.com info@newgatesimms.com