

SMARTINT

Universal Machine Colorants

Series 1400

Technical Data Sheet

Product Code	Shade Name	Canister Code	Pigment %	Viscosity in KU	Specific Gravity (kg/l) ± 0.025	Light Fastness (8 is best)		Weather Fastness (5 is best)	
						FT	RT	FT	RT
1400-0101	Smartint White	XT	65	75 +/- 15	2.00	5	5	8	8
1400-0201	Smartint Black	TT	13	75 +/- 15	1.37	5	5	8	8
1400-0301	Smartint Yellow	KS	25	75 +/- 15	1.30	4-5	4	6-7	6
1400-0302	Smartint Yellow	US	30	75 +/- 15	1.29	4-5	4	6-7	6
1400-0303	Smartint Yellow	ZT	20	75 +/- 15	1.43	5	5	8	8
1400-0401	Smartint Green	LS	29	75 +/- 15	1.34	5	5	8	8
1400-0402	Smartint Green	LT	15	75 +/- 15	1.44	5	5	8	8
1400-0501	Smartint Blue	MS	24	75 +/- 15	1.26	5	5	8	8
1400-0502	Smartint Blue	MT	15	75 +/- 15	1.34	5	5	8	8
1400-0601	Smartint Violet	FT	10	75 +/- 15	1.40	4-5	4	7	6-7
1400-0701	Smartint Red	RS	20	75 +/- 15	1.29	4-5	4	6-7	6
1400-0702	Smartint Red	PT	12	75 +/- 15	1.30	5	5	8	8
1400-0902	Smartint Magenta	MM	18	75 +/- 15	1.20	5	5	7-8	7
1400-1001	Smartint Yellow Oxide	RT	60	75 +/- 15	1.85	5	5	8	8
1400-1101	Smartint Red Oxide	VT	65	75 +/- 15	1.83	5	5	8	8
1400-1301	Smartint Brown Oxide	ST	55	75 +/- 15	1.96	5	5	8	8

This information contained herein is based on data available at the time of preparation and is believed to be reliable by us. It relates only to the designated material and may not be applicable when the product is used in combination with other materials and/or process. No warranty is expressed or implied regarding the accuracy of this data. Chemical properties of this product vary due to a number of factors such as substrate conditions, exposure, coatings and base formulations. Soujanya Color Pvt. Ltd. does not assume any responsibility or liability for any product or method described herein, any errors or omissions made herein, or any loss or damage that may occur from the use of information. Users of this product must take their own determination as to the suitability and completeness of this information for use, health and safety, and protection of the environment.