

Thermal Glass Ratings

IAP-M-24

DBL SLIDER - Majestic

| Package | Details | Sgl or Dbl Strength | Foam | Gas | Spacer | U Factor | SHGC | VT | CRF | Grids |
|--------------|------------------------|---------------------|------|-----------|---------------------|----------|------|------|-----|-------|
| | Clear Glass | SS | No | No | Regular (Tin Plate) | 0.47 | 0.62 | 0.63 | 47 | No |
| | Clear Glass | SS | No | No | Regular (Tin Plate) | 0.47 | 0.55 | 0.56 | 47 | Yes |
| | Clear Glass | DS | No | No | Regular (Tin Plate) | 0.47 | 0.60 | 0.63 | 47 | No |
| | Clear Glass | DS | No | No | Regular (Tin Plate) | 0.47 | 0.54 | 0.56 | 47 | Yes |
| | LowE CS36 | SS | No | No | Regular (Tin Plate) | 0.34 | 0.29 | 0.51 | 53 | No |
| | LowE CS36 | SS | No | No | Regular (Tin Plate) | 0.34 | 0.26 | 0.46 | 53 | Yes |
| | LowE CS36 | DS | No | No | Regular (Tin Plate) | 0.34 | 0.28 | 0.50 | 53 | No |
| | LowE CS36 | DS | No | No | Regular (Tin Plate) | 0.34 | 0.26 | 0.45 | 53 | Yes |
| | LowE CS36 | SS | No | Argon | Regular (Tin Plate) | 0.30 | 0.28 | 0.51 | 56 | No |
| | LowE CS36 | SS | No | Argon | Regular (Tin Plate) | 0.30 | 0.26 | 0.46 | 56 | Yes |
| | LowE CS36 | DS | No | Argon | Regular (Tin Plate) | 0.30 | 0.28 | 0.50 | 56 | No |
| | LowE CS36 | DS | No | Argon | Regular (Tin Plate) | 0.30 | 0.25 | 0.45 | 56 | Yes |
| Energy Smart | LowE CS36 | SS | No | Argon | Stainless Steel | 0.29 | 0.28 | 0.50 | 60 | No |
| | LowE CS36 | SS | No | Argon | Stainless Steel | 0.29 | 0.25 | 0.45 | 60 | Yes |
| Energy Elite | LowE CS28 | SS | Yes | Argon | Stainless Steel | 0.27 | 0.22 | 0.48 | 60 | No |
| | LowE CS28 | SS | Yes | Argon | Stainless Steel | 0.27 | 0.20 | 0.43 | 60 | Yes |
| Energy Green | LowE CS36 | DS | Yes | Argon | Stainless Steel | 0.27 | 0.28 | 0.50 | 60 | No |
| | LowE CS36 | DS | Yes | Argon | Stainless Steel | 0.27 | 0.25 | 0.45 | 60 | Yes |
| ESM | LowE CS36 & CS73 | DS | Yes | Argon | Stainless Steel | 0.24 | 0.27 | 0.45 | 48 | No |
| | LowE CS36 & CS73 | DS | Yes | Argon | Stainless Steel | 0.24 | 0.24 | 0.40 | 48 | Yes |
| ESM + | LowE CS28 & CS73 | DS | Yes | Argon | DuraLite | 0.23 | 0.20 | 0.43 | 51 | No |
| | LowE CS28 & CS73 | DS | Yes | Argon | DuraLite | 0.23 | 0.18 | 0.39 | 51 | Yes |
| R-5 | Triple Glass-LowE CS36 | SS | Yes | Arg/Krypt | Regular (Tin Plate) | 0.20 | 0.24 | 0.38 | 65 | No |
| | Triple Glass-LowE CS36 | SS | Yes | Arg/Krypt | Regular (Tin Plate) | 0.21 | 0.22 | 0.34 | 65 | Yes |
| 3-Kr | Triple Glass-LowE CS36 | SS | Yes | Krypton | Regular (Tin Plate) | 0.19 | 0.23 | 0.37 | 65 | No |
| | Triple Glass-LowE CS36 | SS | Yes | Krypton | Regular (Tin Plate) | 0.20 | 0.21 | 0.33 | 65 | Yes |