

## **Part 1, General (Thin Patch)**

### **1.01 Work Included**

- A. Furnish all materials, labor, tools, and equipment to patch or overlay interior and/or exterior horizontal surfaces as designated by the owner.**

### **1.02 Related Work**

- A. Joint fillers**
- B. Crack repair**
- C. Pavement markings**

### **1.03 Quality Assurance**

- A. Provide a notarized certificate stating that the polymer-modified portland cement mortar meets the specified requirements and have the manufacturer's current printed literature on the specified product.**
- B. Polymer-modified cement mortar shall be tested by a certified testing laboratory, on a batch basis, to assure the product has been manufactured as specified on manufacturer's printed literature.**
- C. Complete laboratory test reports, from an independently qualified testing laboratory, shall be made available for the specified product.**

### **1.04 Delivery, Storage, and Handling**

- A. Deliver the specified product in original, unopened containers with the manufacturer's name, labels, product identification, and batch numbers.**
- B. Store and condition the specified product as recommended by the manufacturer.**

### **1.05 Job Conditions**

- A. Environmental Conditions: Do not apply material in rainfall or if the ambient temperature will fall below 40 degrees F. within 24 hours of application.**
- B. Protection: Precautions should be taken to avoid damage to any surface near the work zone due to mixing and handling of the polymer-modified portland cement mortar.**

## **Part 2, Products**

### **2.01 Acceptable Products**

- A. Thin Patch By U. S. Concrete Products, LLC.**
- B. Substitutions: The use of other than the specified product will be considered providing the contractor requests its use in writing to the Engineer. This request shall be accompanied by a certificate of compliance from an approved independent testing laboratory that the proposed substitute product meets or exceeds the specified performance criteria, tested in accordance with the specified test standards.**

## 2.02 Performance Criteria

- A. Properties of the mixed polymer-modified portland cement mortar:
  - 1. Working Time: 10-15 minutes
  - 2. Finishing Time: 20-60 minutes
  - 3. Color: concrete gray
  - 4. Flow: 100-200% (ASTM C109)
  
- B. Properties of the cured polymer-modified portland cement mortar:
  - 1. Compressive Strength (ASTM C-109 Modified)
    - a. 1 day 2000 psi
    - b. 7 days 4000 psi
    - c. 28 days 6500 psi
  - 2. Splitting Tensile Strength (ASTM C-496) at 28 days: 400 psi min.
  - 3. Flexural Strength (ASTM C-78) at 28 days: 1000 psi min.
  - 4. Bond Strength (ASTM C-882 Modified) at 28 days: 2200 psi min.
  - 5. Thermal Compatibility (ASTM C-884 Modified): passes test min.
  - 6. Abrasion (Taber Abrader) at 7 days.
    - a. Weight Loss: 5.6 gm max. (H-22 wheel; 1000 gm load; 1000 cycles)

## 2.03 Materials

- A. Polymer-modified portland cement mortar:
  - 1. U.S. Thin Patch shall be a blend of selected portland cements, specially graded aggregates admixtures for controlling setting time, water reducers for workability and corrosion inhibitors.
  - 2. The ratio of water: U.S. Thin Patch shall be 1:7.2 by weight.
  - 3. The material shall not contain asbestos, chlorides, nitrates, added gypsum, added lime, or high aluminum cements.
  - 4. The material shall be non-combustible, either before or after cure.
  - 5. The polymer-modified portland cement mortar shall be supplied in a factory proportioned unit.
  - 6. The polymer-modified portland cement mortar must be able to be finished with a power trowel.
  - 7. The polymer-modified portland cement mortar must be placeable from 1/2 in to 1 in. in depth and extendable in greater depths.

## Part 3, Execution

### 3.01 Surface Preparation

- A. The surface must be mechanically prepared. Areas to be patched or overlaid must be clean and sound. All loose and deteriorated concrete shall be removed by mechanical means approved by the Engineer. Chip concrete substrate to obtain a surface profile of + 1/16 in. with a new aggregate fractured surface. Be sure the area to be patched or overlaid is not less than 1/2 in. in depth. Sandblast reinforcing steel to remove all contaminants and rust. Where reinforcing steel is encountered, the following procedures will be used. If half of the diameter of the rebar is exposed, chip out behind the reinforcing steel. The distance chipped behind the rebar will be equal to or exceed the minimum placement depth of the approved material.

- B. Cracks in the substrate in the area of the patching or overlay work must be treated as directed by the Engineer.
- C. Extend all existing control and expansion joints through any patch or overlay. Install new joints as directed by the Engineer. Fill all joints as directed by the Engineer.

### 3.02 Application

- A. **Mixing the polymer-modified portland cement concrete:** Mix manually or mechanically. Manually mix in a wheelbarrow or mortar box. Mechanically mix in appropriate sized mortar mixer or with a jiffy paddle and low speed (400-600) rpm drill. Pour approximately 3/4 gal. water into the mixing container. Add U.S. Thin Patch while continuing to mix. Mix to a uniform consistency for a maximum of three minutes. Add remaining water to mix if a more loose consistency is desired. If manual mixing takes more than three minutes, mix small quantities. Should smaller quantities be needed, be sure the components are dosed in the correct ratio and that the U.S. Thin Patch is uniformly pre-mixed before batching.
- B. **Placement Procedure:** At the time of application, the substrate should be saturated surface dry with no standing water. Mortar and/or concrete must be scrubbed into substrate filling all pores and voids. While the scrub coat is still plastic, force material against edge of repair, working toward center. After filling, consolidate, then screed. Allow mortar to set to desired stiffness. Then finish with trowel, manual or power for smooth surface. Broom or burlap drag for rough surface. Areas where the depth of the repair area to sound concrete is less than 1 in. shall be repaired with polymer-modified portland cement mortar. In areas where the depth of the repair is greater than 1 in., the repair shall be made with polymer-modified portland cement concrete.
- C. Curing is not required under most conditions. However, if ambient condition might cause premature surface drying-high winds, high temperatures, direct sunlight, low humidity, etc., use a fine mist of water or wet burlap.
- D. Adhere to all limitations and cautions for the polymer-modified portland cement mortar in the manufacturers current printed literature.

### 3.03 Cleaning

- A. The uncured polymer-modified portland cement mortar can be cleaned from tools with water. The cured polymer-modified portland cement mortar can only be removed mechanically.

Guide.thinpatch