

RUSCOE

RB-708-R Low VOC Contact Adhesive

RB-7-08 is a high performance contact adhesive that can be used on a variety of substrates. **RB-7-08** is high-solids, and provides a high yield with a smooth spray pattern that reduces telegraphing on thin laminates. It gives a water resistant, non-staining bond for common HPL applications. Formulated for use in bonding a wide variety of materials, including, but not limited to: decorative laminates, metals (not copper), plywood, particleboard, polyurethane foam, and rigid plastics.

FEATURES

- Quick Dry Time
- High Strength Bonds
- Aggressive Grab Tack
- Smooth, flat spray pattern
- High Green Strength
- Long Open Time
- Excellent adhesion to many substrates
- OTC States Compliant

SUSTAINABILITY GUIDE

GREENGUARD® Children & Schools Certified

GREENGUARD® Indoor Air Quality Certified

Contributes to **LEED®** and other green building rating system credits:

- o **LEED-NC** and **LEED-CI EQ Credits 4.1**
- o **LEED for Schools EQ Credit 4**
- o **LEED Core & Shell EQ Credit 4**
- o **LEED-EB MR Credit 3**
- o **CHPS® (Collaborative for High Performance Schools) EQ Credit 2.2**
- o **Green Guide for Health Care EQ Credit 4.1**
- o **NAHB Model Green Home Bldg Guidelines – Sect 7, Global Impact 7.1.3**



REGULATORY COMPLIANCE

- SCAQMD (South Coast Air Quality Management District), Rule 1168
- California Air District Regulations
- Ozone Transport Commission (OTC) Rule for Adhesives and Sealants

DIRECTIONS

Use only after careful consideration of the warnings, directions, and first aid instructions given. Do not thin. Surfaces to be bonded should be clean, dry and free of any dust, loose paint, wax, moisture, dirt, grease, oil, rust, or other contaminants. Stir thoroughly before using. Adhesive should be at 60°F to 95°F. For best results, adhesive and materials to be bonded should be 60°F (15.6°C) to 95°F (35°C) during application. Allow substrates to acclimate to room temperature for 48 hours before bonding.

SPRAY APPLICATIONS: Apply adhesive uniformly to both surfaces and cover each surface a minimum of 80%. Some porous surfaces may require two coats. 100% coverage is recommended for the edges. Use only approved equipment. For typical applications a coating weight of 2.5 - 3.5 dry grams per square foot is recommended. Both surfaces must be allowed to dry before bonding. This will usually take from 2 to 5 minutes at room temperature under normal conditions. Heat and humidity, or cold weather can effect drying times. Surfaces are dry if adhesive is

tacky, but no adhesive transfers to the hand when touched. Complete the bond within 30 minutes (under normal conditions) after the adhesive is dry.

BRUSH APPLICATIONS: Apply the adhesive with a brush or solvent-resistant medium nap roller. Apply adhesive uniformly to both surfaces and cover each surface 100%. Some porous surfaces may require two coats. Double coat all edges. For typical applications a coating weight of 3.0 dry grams per square foot is recommended. Both surfaces must be allowed to dry before bonding. This will usually take from 10 to 15 minutes at room temperature under normal conditions. Heat and humidity, or cold weather can effect drying times. Surfaces are dry if adhesive is tacky, but no adhesive transfers to the hand when touched. Complete the bond within 30 minutes (under normal conditions) after the adhesive is dry. If the two surfaces don't grab immediately when brought into contact, they have dried too long. Position coated surfaces carefully before putting them together since no shifting is possible once contact is made. Bring surfaces together and immediately apply firm pressure over entire surface working from the center to the edges.

Apply a minimum of 30 psi uniform pressure over 100% of the area being bonded. Let bonded parts cure for at least 72 hours before exposing to direct sunlight of temperatures over 150° F (65.6°C). Replace lid after each use and secure tightly for storage. Do not use on some vinyls or polystyrene foam. Some vinyls contain plasticizers, which can, over time, soften and dissolve the bond, or bleed through/dicolor. When in doubt, or if product is to be used on vinyls, or other light colored materials, conduct compatibility testing on the product to be bonded before use.

NOTE: The shelf life for an unopened container of this adhesive stored at temperatures between 60°F (15.6°C) and 95°F (35°C) is 1 year from date of manufacture. Store out of direct sunlight in a cool, well-ventilated area. Avoid storing container directly on the floor or against an outside wall. **ATTENTION:** Empty container remains hazardous until all flammable vapors, which may explode upon ignition, are gone from residue and container. Observe all labeled hazard precautions. Do not cut, puncture, or weld while hazard exists. Do not reuse empty container. Dispose of according to all federal, state, and local regulations.

NOTICE: Reports have associated repeated and prolonged occupational exposure to solvents with permanent brain and nervous system damage.

PHYSICAL PROPERTIES

BASE: Synthetic Polymer VOC CONTENT: 2.30g/L (EPA Method 24)

SHELF LIFE: 1 year from date of manufacture VISCOSITY: 75-225 cps

SOLIDS: 32.0 +/- 2.0% OPEN TIME: 30 minutes

FLASHPOINT: 8.6°F (-13°C) DRY TIME: 2-5 minutes

COLORS: Clear /Red COVERAGE 460 ft²/gallon @2.5 dry grams/ft²

FORMALDEHYDE: No urea formaldehyde added during adhesive manufacturing

APPROVED SPRAY EQUIPMENT

	AUTOMATIC		MANUAL	
	BINKS	DEVILBISS	BINKS	DEVILBISS
Spray Gun:	21,95A	AGX-550	95, 2100	JGA-510, MSA-510
Fluid Tip:	63ASS	FX	63ASS	FX
Fluid Needle:	263A, 763A	FX	663A, 563A	FX
Air Cap:	66SD-3	24	66SD-3	24
Air Atomization Pressure:	70-90 psi, Fluid Pressure: 6-10 psi			
Hot spray temperature:	120°F maximum			

**KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL OR INDUSTRIAL USE ONLY
IF SPRAYING, USE ONLY WITH APPROVED EQUIPMENT
SALE TO CONSUMER IS IN VIOLATION OF FEDERAL LAW**

NOTICE TO PURCHASER: NO WARRANTIES, EXPRESS OR IMPLIED, ARE MADE INCLUDING MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE. EXCEPT FOR PERSONAL INJURY RESULTING FROM USE OF THE PRODUCT AS DIRECTED, THE RUSCOE COMPANY SHALL NOT BE LIABLE IN TORT OR CONTRACT FOR ANY LOSS OR DAMAGE. UNDER NO CIRCUMSTANCES SHALL THE RUSCOE COMPANY BE LIABLE FOR ANY LOSS OR DAMAGE ARISING FROM THE PURCHASE, USE, OR INABILITY TO USE THIS PRODUCT, OR FOR ANY SPECIAL, INDIRECT, INCIDENTAL, OR CONSEQUENTIAL DAMAGES. THE USER MAY SEND A SAMPLE OF PRODUCT TO THE RUSCOE COMPANY FOR TESTING. IF SUCH TESTING PROVES A PRODUCT DEFECTIVE, THE USER'S SOLE AND EXCLUSIVE REMEDY IS EITHER REIMBURSEMENT

OF THE PURCHASE PRICE OF THE PRODUCT OR REPLACEMENT OF THE CONTAINER OF PRODUCT. NO FABRICATOR, INSTALLER, DEALER, AGENT OR EMPLOYEE OF THE RUSCOE COMPANY HAS THE AUTHORITY TO MODIFY THE OBLIGATIONS OR LIMITATIONS OF THIS WARRANTY. This warranty gives you specific legal rights, and you may also have other rights, which vary from state to state; therefore, some of the limitations stated above may not apply to you. It is to your benefit to save your documentation upon purchase of a product. The information and suggestions for use contained herein are believed to be accurate, but are not to be construed as warranties. User shall determine the suitability of the product for his or her intended use and shall assume all risk associated therewith.

Please direct all inquiries regarding performance of this product to:
The Ruscoe Company
Phone 1-800-293-8148
Fax 1-800-253-2933