

## RhinoGuard ESD Spray Buff

for use with RhinoGuard ESD floor finish

This innovative spray buff is formulated as a companion product for RhinoGuard ESD Floor Finish to extend the life of the static dissipating qualities as well as maintain the gloss and enhance the appearance of the floor between recoating with floor finish. RhinoGuard ESD Spray Buff is suitable for use on StaticSmart Summit Series tile flooring.

### SPECIFICATIONS

Nonvolatile Solids	8 ± 0.5%
Total Active	12%
Resistivity-ASTM D257	<10 <sup>9</sup> Ohms <sup>2</sup> Max./Cm <sup>2</sup> @ 40% Relative Humidity
pH	8.0 - 8.8
Gloss 60° - Buffed	85
Color	Translucent white
Weight Per Gallon	7.5-8.5
Slip Resistance (ASTM)	0.52 minimum
Stability	1 year minimum at room temperature
Freeze/Thaw Stability	3 cycles
Drying Time	30 minutes
Water Resistance	Good
Gallon Coverage (Feet <sup>2</sup> )	2000 - 3500 ft <sup>2</sup>
VOC Content	59 Grams/Liter

### SAFETY INFORMATION

Health	1
Flammability	0
Reactivity	0
Personal Protection	B

#### Read Safety Data Sheet Thoroughly Before Using.

This finish is not a hazardous mixture as defined in 29 CFR 1910. Safety glasses and gloves should be worn during application and handling. **FIRST AID:** In the event of skin or eye contact, flush area with water for 15 minutes. If skin irritation occurs, contact a physician. In the event of eye contact or ingestion, seek immediate medical treatment.

### APPLICATION & MAINTENANCE

Remove loose dirt and soil by sweeping or vacuuming. For best results, the area to be buffed should be damp mopped with a neutral Ph cleaner. Using a soft or medium pad, spray RhinoGuard ESD Floor buffing solution ahead of the buffing machine, working only in small areas at a time.

RhinoGuard may also be diluted 32 ounces per gallon of water (1:4) for use as a mop restorer. Dilute the liquid in a mop bucket with cold water. Damp mop the area using a lint-free cotton, or combination cotton and synthetic mop. Allow the floor to dry thoroughly, then burnish with a soft pad. Wash and rinse buffing pads after each application.

**For optimum results, do not apply under high humidity conditions.**