

## **Pink® Soundbreak™** **High performance acoustic insulation**

### **Description**

Pink® Soundbreak™ batts are made from high density, flexible and resilient glasswool, which is specifically designed to provide exceptional acoustic insulation performance of residential ceilings, walls and midfloors. Pink® Soundbreak™ batts are available in various sizes to fit standard timber and steel stud/joist spacings.

### **Application**

Pink® Soundbreak™ batts with its high nominal density of 24–26kg/m³ makes it ideal for reducing sound transfer through walls (both internal and external). Internal walls between theatre rooms, bathrooms, laundries and kitchens are just some of the areas where internal wall insulation could be beneficial. The high density also aids in achieving higher thermal R-values for external walls with limited cavity spaces. The Pink® Soundbreak™ batts insulation range is available in various thermal R-values and dimensions ensuring there is an effective and efficient product solution for all residential applications.

Pink® Soundbreak™ batts, renowned for their firmness, are low itch, easy to cut and friction fit standard studs/joists to make homes feel cooler in summer, warmer in winter and acoustically quiet all year round.

### **Physical Characteristics**

	<b>Material R-value m²K/W</b>	<b>Nominal Thickness mm</b>	<b>Width mm</b>	<b>Length mm</b>	<b>Batts per pack</b>	<b>m² per pack</b>	<b>Coverage per pack m²</b>	<b>Packs per Bale</b>	<b>Product Code</b>
<b>Wall</b>	R1.7	60	430	1160	12	6.0	6.9	5	902191
			580	1160	12	8.1	9.1	5	902192
	R2.0	70	430	1160	10	5.0	5.8	5	902193
			580	1160	10	6.7	7.6	5	902194
			600	1200	10	7.2	7.2	5	902195
	R2.5	90	430	1160	8	4.0	4.5	5	902196
			580	1160	8	5.4	6.1	5	902197
	R2.7	90	430	1160	8	4.0	4.5	5	902198
			580	1160	8	5.4	6.1	5	902199
			600	1200	8	5.8	5.8	5	902200
R3.1	110	430	1160	6	3.0	3.4	5	902201	
		580	1160	6	4.0	4.5	5	902202	

## Physical Properties

Property	Test Method/Standard	Result	Unit
Maximum Service Temperature	ASTM C411/C447	350	°C
Thermal Resistance	AS/NZS 4859.1:2002	Complies	m <sup>2</sup> .K/W
Moisture Absorption	When exposed to environmental conditions of 50°C and 95% relative humidity for four days	<0.2%	% by volume
pH	ASTM C871	9 (does not contribute to the corrosion of steel structures)	–
Density	ASTM C167	24-26	Kg/m <sup>3</sup>

## Fire Hazard Properties

Property	Test Method/Standard	Result
Combustibility	AS1530.1:1994	Non combustible
Ignitability Index	AS/NZS 1530.3:1999	0
Spread of Flame Index		0
Heat Evolved Index		0
Smoke Developed Index		1
BAL Compliance	AS3959:2018	Low – FZ

## Acoustic Performance

Pink® Soundbreak™ batts tested achieve the following Flow Resistivities when tested in accordance with ASTM C522-03.

Thicknesses mm	60	70	90	90	110
R-Value	1.7	2.0	2.5	2.7	3.1

Property	Test Method/Standard	Test Results					Unit
Airflow resistance of acoustic materials	ASTM C522-03	10480	12860	11140	16001	12760	Rayls/m

## Health and Safety

Fletcher Insulation glasswool products are manufactured from FBS-1 Glasswool Bio-Soluble Insulation®. FBS-1 Glasswool Bio-Soluble Insulation® is safe to use and is classified as non-hazardous according to the criteria of Safe Work Australia. Fletcher Insulation glasswool insulation can be used with confidence in any residential, commercial or industrial application.

## Environmental Properties

Fletcher Insulation avoids the use of Ozone Depleting Potential (ODP) substances in the manufacture or composition of its FBS-1 Glasswool Bio-Soluble Insulation® and Sisalation® reflective foil products.

The use of these Fletcher Insulation products guarantees the use of Zero ODP insulation while also ensuring that no harmful levels of Volatile Organic Compounds (VOCs) are released. This allows the incorporation of environmentally preferable insulation whilst also maintaining indoor air quality.

## Technical Specification

When specifying, state the following:

The insulation material shall be Fletcher Insulation Pink® Soundbreak™ R \_\_\_\_\_ m<sup>2</sup>K/W (Material R-value) \_\_\_\_\_ (thickness) x \_\_\_\_\_ (width) x \_\_\_\_\_ (length) mm. Compliant with the thermal testing requirements of AS/NZS 4859.1:2002, and non-combustible according to AS1530.1:1994 (R2016).

© Fletcher Insulation Pty Limited 2019. Fletcher Insulation reserves the right to change product specifications without prior notification. Information in this publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application. The colour PINK, Pink® and Pink® Batts are registered trademarks of Owens Corning used under licence by Fletcher Insulation. FBS-1 Glasswool Bio-Soluble Insulation® is a registered trademark of ICANZ. Unless otherwise stated all ™ and ® are trademarks and registered trademarks of Fletcher Insulation Pty Limited ABN 72 001 175 355. RTDS3\_Revision\_3\_Issue Date 08102019.

For more information call 1300 654 444  
email [info@insulation.com.au](mailto:info@insulation.com.au) or web [www.insulation.com.au](http://www.insulation.com.au)

