



TECHNICAL DATA SHEET

485 KENMORE BLVD.
AKRON, OH 44301-1013
WEB SITE: www.ruscoe.com

THE RUSCOE COMPANY
P.O. BOX 3858
AKRON, OH 44314-0858
E-MAIL: sales@ruscoe.com

PHONE: 330-253-8148
FAX: 330-253-2933
TOLL FREE: 800-293-8148

Clear PVC Cut Edge Sealant

Ruscoe's Clear PVC Cut Edge Sealant is a solution of plasticized, UV stabilized, polyvinyl chloride resin. This product can be used to seal the cut edges of PVC roofing membranes or swimming pool liners.

PROPERTIES:

Solids	15-20%
Viscosity	540-940 cps (Brookfield RVF #3 @ 20 rpm)
Density	7.6-7.8 #/gal
Solvents	Tetrahydrofuran

SURFACE PREPARATION:

Surfaces should be reasonably free of moisture, dirt, dust and other contamination. Wipe membrane with low VOC membrane cleaner if necessary.

APPLICATION:

Shake bottle or stir material in can. Apply a bead of sealant directly to the cut edge of the membrane ensuring that any exposed fibers or voids are fully covered.

DRYING:

Films or thin beads will be reasonably dry in 30 minutes to 1 hour at 50-90°F with low to moderate humidity. Colder or more humid days may require longer drying time before the coating or bead is tack free. Allow 24-48 hours or more for thick beads of sealant to fully cure/dry.

CLEANING:

Clear PVC Cut Edge Sealant can be cleaned using tetrahydrofuran or cyclohexanone.

STORAGE:

Clear PVC Cut Edge Sealant is flammable and should be stored below 100°F (37.7°C) in tightly sealed containers away from direct sunlight, heat, sparks, or other potential sources of ignition. Shelf life is 12 months from date of manufacture when stored appropriately. See Safety Data Sheet for more information on storage and disposal.

All statements, technical information and recommendations contained herein are based on tests believed to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties expressed or implied.

Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of, or the inability to use the product. Before using, user shall determine the suitability of the product for their intended use and user assumes all risk and liability whatsoever in connection therewith.

The foregoing may not be changed except by an agreement signed by officers of seller or manufacturer. February 2019