



Rasaplast Non-Cementitious Base Coat

TECHNICAL DATA

REPORT	TEST METHOD	TEST CRITERIA	TEST RESULTS
Surface Burning	ASTM E-84	< 25 Flame Spread	Pass
		< 450 Smoke Developed	Pass
Adhesion (psi)	ASTM C-297	28 days	> 25 Gypsum Sheathing > 13 EPS Board > 90 Concrete Block > 30 DensGlass® Gold > 50 Concrete
Water Absorption (oz/ft ² /hr) [kg/m ² /hr]	Lab Method	28 days	0.331 [0.099]
Flexural Strength (psi) [kPa]	ASTM C-203	28 days	65 [448]
Accelerated Weathering	ASTM G-23	2000 hours	Pass

Rasaplast is a Non-Cementitious Base Coat, ready-mixed 100% acrylic non-cementitious embedding base coat.

Coverage

165 - 250 ft² (15.3-23.2m²) at the recommended dry thickness of 1/16" (1.6 mm) as an embedding or skim coat.

Not recommended for use as an adhesive.

Coverages may vary depending on application technique and surface conditions.

FEATURES BENEFITS

100% Acrylic Polymer-modified	Flexural strength, resists cracking, increased finish coverage
Smooth consistency	Trowels on easily; increases productivity
Vapor permeable	Allows substrate to breathe naturally; resists blistering due to vapor
Ready-mixed	Ready to use; no cement added at job site
Low VOC	Safe for workers and the environment

Packaging

5 gal. (19L) pail 62.5 lbs / 28.4 kg per pail

Shelf Life

24 months, if unopened, properly stored and protected from moisture.

Storage

Store off the ground in a dry area. Protect from extreme heat [90°F (32°C)], moisture and direct sunlight.

SURFACE PREPARATION

As a Base Coat

Concrete / Masonry / Brick

Surfaces must be clean, dry and free of frost, damage and all bond inhibiting materials, including dirt, efflorescence, laitance, form oil and other foreign matter. Loose or damaged material must be removed by water blasting, sandblasting or mechanical wire brushing and repaired. Avoid application over irregular surfaces. Resurface, patch or level surfaces to required tolerance and smoothness with appropriate Decoplast leveling materials.

Rasaplast Non-Cementitious Base Coat



MIXING

Mix with a clean, rust-free electric drill and paddle. **DO NOT ADD WATER.**

APPLICATION

Apply only to sound and clean, dry, properly prepared, frost-free surfaces.

As a Base Coat:

Apply with a stainless steel trowel to an approximate thickness of 1/8" (3 mm). Work horizontally or vertically in strips of 40" (1 m) and immediately embed Decoplast Reinforcing Mesh in wet base coat by troweling from the center to the edges of the mesh. Avoid wrinkles in the mesh and smooth the base coat to eliminate trowel marks. Minimum recommended dry thickness of the reinforced base coat is 1/16" (1.6 mm) when dry. Reapply additional base coat if necessary to achieve minimum thickness as soon as the first application is dry. Embedded mesh in base coat should not be visible.

Crack Repair

Embed Decoplast Reinforcing Mesh centered over the crack in Decoplast Reinforcing Mesh and feather along edges.

Curing/Drying

Dries within 24 hours under normal drying conditions [70°F (21°C), 50% RH]. Allow additional drying time during cold, humid, or wet weather until insulation board is fully adhered before rasping, and before application of primer or finish to hardened Base Coat. Protect from rain, freezing and continuous high humidity until completely dry. Decoplast recommends using Decoplast Primer prior to application of finish.

Clean Up

Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

LIMITATIONS

Use Rasaplast Base Coat only when surface and ambient temperatures are above 40°F (4°C) and below 100°F (38°C) during application and drying period.

Sloped surfaces: Refer to Decoplast details.

Rasaplast Base Coat should not be used on weather-exposed horizontal or below grade surfaces or where immersion in water may occur.

Rasaplast Base Coat should not be used as a finish coating.

HEALTH AND SAFETY

Health Precaution

Rasaplast Non-Cementitious Base Coat is water based. As with any chemical construction product, exercise care when handling.

WARNING!

Causes eye and skin irritation.

Safety Precaution

Wash hands thoroughly after handling. Wear protective gloves/protective clothing/eye protection/face protection.

First Aid:

EYE CONTACT: Immediately flush eyes with plenty of water for at least 15 to 20 minutes. Ensure adequate flushing of the eyes by separating the eye lids with fingers. Get immediate medical attention.

SKIN CONTACT: Immediately wash skin with plenty of soap and water for at least 15 to 20 minutes, while removing contaminated clothing and shoes. Get medical attention if irritation develops or persists.

INHALATION: If inhaled, remove to fresh air. If not breathing give artificial respiration or give oxygen by trained personnel. Seek medical attention immediately.

INGESTION: If swallowed, do NOT induce vomiting. Call a physician or a poison control center immediately. Never give anything by mouth to an unconscious person.

Spills

Contain and collect in an appropriate container. Uncured material may be removed with water.

Disposal

Dispose of in accordance with local, state or federal regulations.

Warning

KEEP CONTAINER CLOSED WHEN NOT IN USE. KEEP OUT OF THE REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. Consult the Safety Data Sheet (SDS) for further health and safety information.

LIMITED WARRANTY

This product is subject to a written limited warranty. Refer to Decoplast Specifications for more complete information on proper use and handling of this product.



697 Oakwood Avenue, West Hartford, CT 06110
voice: 860.761.2830 fax: 860.761.2831
www.decoplast.com

This product is intended for use by qualified professional contractors. All information conforms to the standard detail recommendations and specifications for the installation of Decoplast systems and is presented in good faith as of the date of publication of this document. GREENMAKER INDUSTRIES ASSUMES NO LIABILITY, EXPRESSED OR IMPLIED, AS TO THE WORKMANSHIP, ENGINEERING OR ARCHITECTURE OF ANY PROJECT. For more information regarding this product or additional Decoplast products, please contact a Decoplast Representative at (860) 761-2830 or visit our website www.Decoplast.com.